

18

Permissible Variations in Dimensions for Hot Finished Flat Bars

	Permissible Variations in Thickness											
Flat Bar Width to 1"	<u>Over</u> 0.015"	<u>under</u> 0.015"	1/8" t <u>Over</u> 0.008"	to 1/2" <u>under</u> 0.008"	Over 1/ <u>Over</u> 0.010"	⁽ 2" to 1" <u>under</u> 0.010"	Over ´ <u>Over</u>	I" to 2" <u>under</u>	Over 2 <u>Over</u>	2" to 4" <u>under</u>	Over 4 <u>Over</u>	4" to 6" <u>under</u>
Over 1" to 2"	0.031"	0.031"	0.012"	0.012"	0.015"	0.015"	0.031"	0.031"				
Over 2" to 4"	0.062"	0.031"	0.015"	0.015"	0.020"	0.020"	0.031"	0.031"	0.062"	0.031"		
Over 4" to 6"	0.093"	0.062"	0.015"	0.015"	0.020"	0.020"	0.031"	0.031"	0.062"	0.031"	0.093"	0.062"
Over 6" to 8"	0.125"	0.156"	0.016"	0.016"	0.025"	0.025"	0.031"	0.031"	0.062"	0.031"	0.093"	0.062"