

Fidelity Stainless



855 Steeles Avenue East, Milton, Ontario L9T 5H3
Phone: (289)-851-1076 Fax: (289)-851-1079

304/L Angle

MATERIAL SPECIFICATIONS

PREPARED BY: M POPE

REVISION DATE: 05/25/23

MATERIAL	STAINLESS ANGLE BAR 304/304L R/L 20'-24'	HOT ROLLED, ANNEALED AND PICKLED DUAL CERTIFIED
-----------------	---	--

SPECIFICATIONS	ALL SPECIFICATIONS WITH LATEST YEAR REVISIONS AISI 304,304L UNS# S30400/S30403, ASTM A182, ASTM A262 PRACTICE E, ASTM A276, ASTM A314, ASTM A479, ASTM A484 ASME SA182, ASME SA479, ASME SA484, AMS 5639, AMS 5647, QQ-S-763F COND A, EN 10204-3.1
-----------------------	--

<u>CHEMICAL ANALYSIS</u>	<u>MECHANICAL PROPERTIES</u>
Carbon (C) .03	Tensile Strength 75 KSI (U.T.S.)
Chromium (Cr) 18.00/20.00	Yield Strength 30KSI (Yield)
Cobalt (Co) aim .10 max	Elongation 40% (Ei. or Elong.)
Copper (Cu) 1.00 aim .75 max	Reduction of Area 50% (R.A. or Red.)
Manganes (Mn) 2.00	Hardness 140/241 BHN (RB,RC,or BHN,HB)
Molybdenum (Mo) 1.00 aim .75 max	(Aim 170-223)
Nickel (Ni) 8.00/10.50	
Nitrogen (N) .10	
Phosphorous (P) .045	
Silicon (Si) 1.00	
Sulfur (S) .03 aim .02-.03	

All singular chemistry values are
MAXIMUM unless otherwise noted

All mechanical properties are
MINIMUM unless otherwise noted

OTHER TEST(S) AND/OR REQUIREMENTS

INTERGRANULAR CORROSION TEST (FREE FROM CONTINUOUS CARBIDE)

AS PER ASTM A262-01 PRACTICE E

MACRO ETCH TEST & MICRO STRUCTURE TO BE SATISFACTORY AS PER QQS-763

MERCURY FREE CONTAMINATION STATEMENT

FREE FROM RADIOACTIVE CONTAMINATION STATEMENT.

NO WELDING OR WELD REPAIR STATEMENT

REPORT GRAIN SIZE PER ASTM E112-96

SOLUTION ANNEALED CONDITION A PER ASTM A479 AT 1040C/1900F MINIMUM AND WATER QUENCHED

HEAT TREATMENT TEMPERTURE, TIME (HOURS SOAKED) AND COOLING MUST BE REPORTED,

FINISHED CONDITION, MELT AND HOT WORKING PRACTICES (FORGED OR ROLLED) MUST BE REPORTED.

GRADE AND HEAT NUMBER MUST BE METAL STAMPED AT BOTH ENDS ON SIZES 1" DIA. AND LARGER

COLOUR CODE RED

BUNDLE WEIGHT - 2200 LBS MAXIMUM. ONE HEAT PER SIZE PER BUNDLE.

IMPORTANT:

ORIGINAL CERTIFICATES OF CHEMICAL & PHYSICAL ANALYSIS REQUIRED TWO (2) WEEKS BEFORE SHIPMENT ARRIVES

ALL TEST REPORTS MUST STATE COUNTRY OF ORIGIN

TEST REPORTS MUST HAVE THE SIGNATURE NAME AND TITLE PRINTED

ALL TEST REPORTS MUST BE SIGNED BY AUTHORIZED PERSON