

855 Steeles Avenue East, Milton, Ontario L9T 5H3 Phone: (289)-851-1076 Fax: (289)-851-1079

## 304/L WELDED PIPE

MATERIAL SPECIFICATIONS PREPARED BY: M POPE REVISION DATE: 05/25/23

MATERIAL	304/304L STAINLESS STEEL WELDED PIPE		COLD/HOT FINISHED						
	LENGTH 20' PLAIN ENDS		DUAL CERTIFIED						
-									
SPECIFICATIONS	ALL SPECIFICATIONS WITH LATEST YEAR REVISIONS  ASTM A 312, ASTM A262 PRACTICE E, ASTM A 999  ASME SA 312, NACE MR 0175, NACE MR 0103, EN 10204 3.1								
					CHEMICAL ANALYSIS	MECHANICAL PROPERTIES			
					CHEWICAL ANALTSIS		MECHANICAL PROP	EKIIES	
Carbon ( C)	.035	Tensile Strength	75 KSI	515 Mpa					
Manganses (Mn)	2.00								
Phosphorus (P)	.045	Yield Strength	30 KSI	205 Mpa					
Sulfur (S)	.03								
Silicon (Si)	1.00	Elongation	35%						
Chromium (Cr)	18.00-20.00	2 inch min %							
Nickel (Ni)	8.00-13.00								
Molybdenum (Mo)	2.00-3.00								
Titanium (Ti)		Hardness	90 HRB	maximum					
Nitrogen (N)									
Copper (Cu)									
Cobalt (Co)									

Other
All singular chemistry values are
MAXIMUM unless otherwise noted

All singular mechanical values are MINIMUM unless otherwise noted

## OTHER TEST(S) AND/OR REQUIREMENTS

BEND AND FLATTENING TEST

ULTRASONIC, EDDY CURRENT, OR HYDROSTATIC PRESSURE TESTED

TYPE OF NON-DESTRUCTIVE ELECTRIC TEST PREFORMED, OR ACTUAL HYDROSTATIC

TEST PRESSURE FOR MATERIAL SUBJECT TO THIS TEST.

MERCURY FREE CONTAMINATION STATEMENT

NO RADIOACTIVE CONTAMINATION STATEMENT

SOLUTION ANNEALED TEMP. 1900 F / 1040 C MINIMUM AND WATER QUENCHED OR RAPIDLY COOLED

HEAT TREATMENT, FINISHED CONDITION AND MELTING PROCESS MUST BE REPORTED.

PLAIN ENDS, 20 FOOT LENGTHS

ALL PIPE TO BE CONTINUOUSLY LINE MARKED. MARKING INK MUST NOT CONTAIN HALOGENS.

EACH SIZE AND HEAT MUST BE BUNDLED SEPARATELY AND CLEARLY TAGGED

STANDARD SEA WORTHY PACKING. COMPLETELY WRAPPED WITH LIFTING NYLON STRAPS

BUNDLE WEIGHT 2000 LBS MAXIMUM

## **IMPORTANT:**

ORIGINAL CERTIFICATES OF CHEMICAL & PHYSICAL ANALYSIS REQUIRED TWO (2) WEEKS BEFORE SHIPMENT ARRIVES

ALL TEST REPORTS MUST STATE COUNTRY OF ORIGIN

TEST REPORTS MUST HAVE THE POSITION AND NAME OF AUTHORIZED PERSON PRINTED

ALL TEST REPORTS MUST BE SIGNED

ISO CERTIFIED STATEMENT